

ステンレス鋼板単重表							
寸法	比重			7.75	7.70	7.93	7.98
	代表鋼種			sus403	sus430	sus304	sus316・L
	(m/m)	(m)	(m)	kg	kg	kg	kg
	0.3	1	2	4.65	4.62	4.76	4.79
	0.4	1	2	6.20	6.16	6.34	6.38
	0.5	1	2	7.75	7.70	7.93	7.98
	0.6	1	2	9.30	9.24	9.52	9.58
	0.7	1	2	10.8	10.8	11.1	11.2
	0.8	1	2	12.4	12.3	12.7	12.8
	0.9	1	2	14.0	13.9	14.3	14.4
	1.0	1	2	15.5	15.4	15.9	16.0
	1.2	1	2	18.6	18.5	19.0	19.2
	1.5	1	2	23.2	23.1	23.8	23.9
	2.0	1	2	31.0	30.8	31.7	31.9
	2.5	1	2	38.8	38.5	39.6	39.9
	3.0	1	2	46.5	46.2	47.6	47.9
	3.5	1	2	54.2	53.9	55.5	55.9
	4.0	1	2	62.0	61.6	63.4	63.8
	4.5	1	2	69.8	69.3	71.4	71.8
	5.0	1	2	77.5	77.0	79.3	79.8
	6.0	1	2	93.0	92.4	95.2	95.8
	7.0	1	2	108.0	108.0	111.0	112.0
	8.0	1	2	124.0	123.0	127.0	128.0
	9.0	1	2	140.0	139.0	143.0	144.0
	10.0	1	2	155.0	154.0	159.0	160.0
	12.0	1	2	186.0	185.0	190.0	192.0
	15.0	1	2	232.0	231.0	238.0	239.0

(注)1,219m/m×2,438m/m(4'×8')は1.5倍、
1524m/m3048m/m(5'×10')は2.3倍で概算値が
えられます